

RECEIVED  
CENTRAL FAX CENTER  
AUG 07 2008

IN THE CLAIMS

Claims 1-34 (canceled)

35. (new) A process comprising coating a surface of a metallic object with an aqueous, acidic composition to form a coated metal, wherein said aqueous, acidic composition comprises:

8 to 50 g/l of phosphate, calculated as  $\text{PO}_4$ ,

0.5 to 30 g/l of zinc ions,

0 to 5 g/l of manganese ions,

0 to 8 g/l of calcium ions,

0 to 5 g/l of magnesium ions,

wherein at least 0.1 g/l of calcium or/and magnesium ions are present,

0.1 to 5 g/l of nitroguanidine,

0 to 2 g/L  $\text{NO}_3$ ,

0 to < 0.8 g/L  $\text{NO}_2$ ,

0.1 to 10 g/l in total of at least one of chlorate or peroxide ions,

in total 0 to 16 g/l of complex fluoride ( $\text{MeF}_4$  or/and  $\text{MeF}_6$ ) of  $\text{Me} = \text{B}, \text{Si}, \text{Ti}, \text{Hf}$

or/and Zr and

0 to 5 g/l of fluoride ions

wherein the total content of complex fluoride and fluoride ions is in the range from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1; and cold forming the coated metal.

36. (new) A process according to claim 35, wherein the composition comprises not more than 1 g/l of nitrate.

37. (new) A process according to claim 35, wherein the composition comprises not more than 0.5 g/l of nitrite.

38. (new) A process according to claim 35, wherein the composition comprises complex fluoride or/and fluoride ions to magnesium ions in a ratio of ( $\text{MeF}_4$ ,  $\text{MeF}_6$  or/and  $\text{F}^-$ ) : Mg in the range from 0.1 : 1 to 10 : 1.

39. (new) A process according to claim 35, wherein the composition comprises complex fluoride or/and fluoride ions to calcium ions in a ratio of ( $\text{MeF}_4$ ,  $\text{MeF}_6$  or/and  $\text{F}^-$ ) : Ca in the range from 0.1 : 1 to 10 : 1.

40. (new) A process according to claim 35, wherein the composition further comprises up to 2 g/l nickel ions.

41. (new) A process according to claim 35, wherein the composition comprises chloride ions in the range up to 5 g/l.

42. (new) A process according to claim 35, wherein the composition further comprises up to 2 g/l sulfate ions.

43. (new) A process according to claim 35, wherein the composition comprises fluoroborate.

44. (new) A process according to claim 24, wherein the composition comprises from 0.1 to 5 g/l  $\text{BF}_4$ .

45. (new) A process according to claim 24, wherein the composition comprises from 0.2 to 3 g/l  $\text{BF}_4$ .

46. (new) A process according to claim 35, wherein the pH of the composition is maintained in the range from 0.1 to 4.

47. (new) A process according to claim 35, wherein a phosphate layer which has at least one of a layer thickness in the range from 0.02 to 15  $\mu\text{m}$  or a layer weight in the range from 0.5 to 25  $\text{g/m}^2$  is formed on said surface.

48. (new). A process according to claim 35, wherein a phosphate layer which has an average edge length of the phosphate crystals of less than 20  $\mu\text{m}$  or even of less than 10  $\mu\text{m}$  and at the same time has a layer thickness with a layer weight in the range of 1.5 to 18  $\text{g/m}^2$  is formed on the surface.

49. (new) A process according to claim 48, wherein the layer weight is from 2 to 15  $\text{g/m}^2$ .

50. (new) A process according to claim 35, wherein after the formation of the phosphate layer at least one layer comprising lubricant is applied.

51. (new) A process for coating surfaces of metallic objects with a phosphating solution to form a coated metal, wherein the ratio of the pickling corrosion on the metallic surface, measured in  $\text{g/m}^2$ , to the layer weight of the phosphate layer, measured in  $\text{g/m}^2$ , lies at values below 75% and wherein the ratio of free acid to total acid of said solution is from 0.25:1 to 0.11 to 1, and coldforming the coated metal.

52. (new) An aqueous phosphating solution comprising:

8 to 100 g/l of phosphate, calculated as  $\text{PO}_4$ ,

0.5 to 60 g/l of zinc ions,

0 to 10 g/l of manganese ions,

0 to 16 g/l of calcium ions,

0 to 10 g/l of magnesium ions,

wherein at least 0.1 g/l of at least one of calcium or magnesium ions are present,

0.05 to 10 g/l of nitroguanidine,

0 to 2 g/l of nitrate,

0.1 to 10 g/l in total of chlorate or/and peroxide ions,

in total 0 to 16 g/l of complex fluoride ( $\text{MeF}_4$  or/and  $\text{MeF}_6$ ) of  $\text{Me} = \text{B}, \text{Si}, \text{Ti}, \text{Hf}$

or/and Zr and

0 to 5 g/l of fluoride ions

wherein the total content of complex fluoride and fluoride ions is in the range from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1.

53. (new) A metallic object coated produced by the process of claim 35 that is coldformed.

54. (new) A process comprising coating a surface of a metallic object with an aqueous, acidic composition to form a coated metal, wherein the aqueous, acidic, composition consists essentially of:

8 to 50 g/l of phosphate, calculated as  $\text{PO}_4$ ,

0.5 to 30 g/l of zinc ions,

0 to 5 g/l of manganese ions,

0 to 8 g/l of calcium ions,

0 to 5 g/l of magnesium ions,

wherein at least 0.1 g/l of calcium or/and magnesium ions are present,

0.1 to 5 g/l of nitroguanidine,

0.1 to 10 g/l in total of chlorate or/and peroxide ions,

in total 0 to 16 g/l of complex fluoride ( $\text{MeF}_4$  or/and  $\text{MeF}_6$ ) of  $\text{Me} = \text{B}, \text{Si}, \text{Ti}, \text{Hf}$

or/and Zr and

0 to 5 g/l of fluoride ions

wherein the total content of complex fluoride and fluoride ions is in the range from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1, and coldforming the coated metal.

55. (new) A process comprising coating a surface of a metallic object with an aqueous, acidic composition to form a coated metal, wherein the aqueous, acidic composition consists of:

8 to 50 g/l of phosphate, calculated as  $\text{PO}_4$ ,

0.5 to 30 g/l of zinc ions,

0 to 5 g/l of manganese ions,

0 to 8 g/l of calcium ions,

0 to 5 g/l of magnesium ions,

wherein at least 0.1 g/l of calcium or/and magnesium ions are present,

0.1 to 5 g/l of nitroguanidine,

0.1 to 10 g/l in total of chlorate or/and peroxide ions,

in total 0 to 16 g/l of complex fluoride ( $\text{MeF}_4$  or/and  $\text{MeF}_6$ ) of  $\text{Me} = \text{B}, \text{Si}, \text{Ti}, \text{Hf}$

or/and Zr and

0 to 5 g/l of fluoride ions

wherein the total content of complex fluoride and fluoride ions is in the range from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1.

56. (new) An aqueous phosphating solution consisting essentially of:

8 to 100 g/l of phosphate, calculated as  $\text{PO}_4$ ,

0.5 to 60 g/l of zinc ions,

0 to 10 g/l of manganese ions,

0 to 16 g/l of calcium ions,

0 to 10 g/l of magnesium ions,

wherein at least 0.1 g/l of calcium or/and magnesium ions are present,  
0.05 to 10 g/l of nitroguanidine,  
0 to 2 g/l of nitrate,  
0.1 to 10 g/l in total of chlorate or/and peroxide ions,  
in total 0 to 16 g/l of complex fluoride (MeF<sub>4</sub> or/and MeF<sub>6</sub>) of Me = B, Si, Ti, Hf  
or/and Zr and  
0 to 5 g/l of fluoride ions  
wherein the total content of complex fluoride and fluoride ions is in the range  
from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1.

57. (new) An aqueous phosphating solution consisting of:

8 to 100 g/l of phosphate, calculated as PO<sub>4</sub>,  
0.5 to 60 g/l of zinc ions,  
0 to 10 g/l of manganese ions,  
0 to 16 g/l of calcium ions,  
0 to 10 g/l of magnesium ions,  
wherein at least 0.1 g/l of calcium or/and magnesium ions are present,  
0.05 to 10 g/l of nitroguanidine,  
0 to 2 g/l of nitrate,  
0.1 to 10 g/l in total of chlorate or/and peroxide ions,  
in total 0 to 16 g/l of complex fluoride (MeF<sub>4</sub> or/and MeF<sub>6</sub>) of Me = B, Si, Ti, Hf  
or/and Zr and  
0 to 5 g/l of fluoride ions

wherein the total content of complex fluoride and fluoride ions is in the range from 0.1 to 18 g/l and wherein the ratio of free acid to total acid is from 0.25:1 to 0.11 to 1.